

Tar Roof Resaturant

PG-0026

Description

Durapax Tar Roof Resaturant is a blend of refined coal tar pitch, aromatic solvents, non-asbestos fibers and fillers, and wet adhesion surfactants, designed for compatibility with and rejuvenation of coal tar pitch roofing systems.

Features

- Highly resistant to chemical and ultraviolet attack.
- Extends the life of coal tar pitch roofing systems.
- Unique self-healing properties and ponding water resistance make it ideal for no to low slope roofs.
- Meets current VOC requirements, except for California.
- Non-Asbestos
- Cold applied with a trowel, brush or spray equipment.
- Federal Specification SS-540A (except, non-asbestos).

Uses

- A cold applied coating/resaturant for use with coal tar pitch BUR roofing.
- Waterproofing and dampproofing of concrete and masonry surfaces.

Application

- Stir mechanically for 5 minutes. Do not heat. Do not thin.
- In cold weather, store product at 70-80° F for 24 hours prior to application or use an OSHA approved pail/drum heater.

Surface Preparation

- All surfaces must be clean, dry, free of heavy dirt, dust, debris, oils, loose gravel, un-adhered coatings, loose, scaling rust, deteriorated membranes, and other contaminants that may result in a surface that is not sound.
- Surface must be free of frost, snow and ice.
- Aggregate must be spud away to provide a proper work surface.
- Fasteners must be repaired and/or replaced as needed.
- If a primer is required, use Durapax Tar Primer.
- Repair blisters, splits, etc.

Application Directions

- Apply to the prepared surface at a rate of 2-4 gallons per square if used as a coating over metal or composition roofs.

- Apply to the prepared coal tar gravel surfaced roof at a rate of 4-7 gallons per square.
- Re-embed gravel.

Application Precautions

- DO NOT use on or with 100% rubber or plastic substrates.
- DO NOT use on or with products containing asphalt.
- DO NOT use where this product may come in contact with potable water.
- DO NOT THIN.
- EXTERIOR USE ONLY.

Clean Up

- Immediately rinse/flush equipment and tools with an OSHA approved aromatic solvent after use, exercising all flammable liquid precautions.
- Use waterless hand cleaner on skin.

Typical Properties

Property	Test Method	Result
Wt/gal, lbs.	D6511	9.6-10.0
Solids, % by wt	D6511	73-77
% by vol		65-69
pH		N/A
Flash Point, °F	PMCC	105 minimum
Color, uncured & cured	Visual	Black
Drying time, Touch	70 °F/50% R.H.	8 hours
Shelf life	70 °F/50% R.H.	1 year
VOC	EPA Method 24A	200 gm/liter max.

Packaging

- 5-gallon pails (52 lbs.).

Specification Compliances

- Federal Specification SS-C-540A (except, non-asbestos).

Safety and Environmental Precautions

- Consult MSDS for detailed handling and disposal.